



Shelf Life of CENTELLEN® and EUROPIIL® gasket material

Shelf life of CENTELLEN® WS 3820, CENTELLEN® HD 3822, CENTELLEN® R 3825, CENTELLEN® NP 3860 and EUROPIIL® 3640

Compressed non asbestos gasket materials are like all elastomer-containing materials subject to a natural ageing process. This process depends on the kind of elastomer, its vulcanisation system and the storage conditions.

Basically a storage according to ISO 2230 (Rubber products – Guidelines for storage) is recommended.

Unfavourable storage conditions can lead to a premature reduction of the materials quality. Especially there is to mention elevated temperature, too low humidity as well as strong illumination.

Storage conditions according to ISO 2230:

- » Storage according to the “First In – First Out” principle
- » Temperature < 25 °C
- » Relative humidity < 65 %
- » Storage room without direct sunlight
- » No contact with metals

According to the storage conditions defined in the ISO 2230 a storage of 7 years for CENTELLEN® WS 3820, CENTELLEN® HD 3822, CENTELLEN® R 3825, CENTELLEN® NP 3860 and EUROPIIL® 3640 is possible.

Actually there is no possibility to define the changing of the storage time due to changes of the 3 influencing factors (temperature, humidity, illumination).

The main influencing factor is certainly the temperature in the storage area.

If the temperature in the storage area is 10 °C higher than ideal (= 25 °C) for a longer time the ISO 2230 defines a reduction in storage time of 50 %.

We therefore recommend a conditioning of the storage area according to ISO 2230.

Ready made gaskets should be stored horizontal as – particularly for bigger gasket sizes – tensions and distortions can occur and complicate the installation.

All information and recommendations contained in this data sheet are to the best of our knowledge correct. Since conditions of use are beyond our control, users must satisfy themselves that the products are suitable for the intended processes and uses. No warranty is given or implied in respect of information or recommendations or that any use of products will not infringe rights belonging to other parties. In any event or occurrence our liability is limited to our invoice value of the goods delivered to you by us. We reserve the right to change product design and properties without notice..

Certified acc. to DIN EN ISO 9001:2015 Subject to technical alterations. Status: February 2023

Rich. Klinger Dichtungstechnik GmbH & Co KG » Am Kanal 8-10 » A-2352 Gumpoldskirchen, Austria
Tel +43 (0) 2252/62599-137 » Fax +43 (0) 2252/62599-296 » e-mail: marketing@klinger.co.at



www.centellen.eu